




**TRUMPLER**
























SIMPLY GOOD CHEMISTRY

LEATHER DYESTUFFS

---

COLORANTES PARA CUERO



















Dyestuff Colorante	Retained 0,5%	Retained 4,0%	Split	Penetration	Light	Solubility	Metal content	PVC	Perspiration		Washing	
								PUD	PUH			
TRUPOCOR Yellow/Amarillo R				3	3	30	MF	5	3	2-3	Ch	
								5	4	4-5	W	
								2	5	5	C	
TRUPOCOR Yellow/Amarillo RCO				3-4	4	50	Cr	4-5	4	4	Ch	
								5	3-4	4-5	W	
								3	4	3	C	
TRUPOXANE Orange/Amaranjado 3TC				4	5	100	Cr	5	5	4	Ch	
								5	4-5	5	W	
								5	5	5	C	
TRUPOXANE Orange/Amaranjado TRL				3	4-5	100	Cr	5	4	4-5	Ch	
								5	3-4	4-5	W	
								3	3	4-5	C	
TRUPOCOR Orange/Amaranjado GS				3-4	4	100	Cr	3-4	4	3-4	Ch	
								5	4	4-5	W	
								2	4	2-3	C	
TRUPOCOR Red/Rojo GE				3	2	40	MF	4-5	4-5	3	Ch	
								4-5	3-4	3-4	W	
								2	4	4-5	C	
TRUPOCOR Red/Rojo 4BS				4	3	75	MF	4-5	5	4-5	Ch	
								5	4-5	5	W	
								4-5	3-4	2-3	C	
TRUPOCOR Red/Rojo ENN				3	2-3	30	MF	4-5	5	4	Ch	
								5	3-4	4	W	
								3	3	3	C	
TRUPOCOR Red/Rojo 2B				4	2-3	100	MF	4-5	4	3-4	Ch	
								4-5	2-3	3-4	W	
								2	3	5	C	
TRUPOXANE Red/Rojo BM				4	3-4	75	MF	5	5	4-5	Ch	
								4-5	4-5	5	W	
								2	3-4	4	C	

Dyestuff Colorante	Retained 0,5%	Retained 4,0%	Split	Penetration	Light	Solubility	Metal content	PVC	Perspiration		Washing	
								PUD	PUH			
TRUPOCOR Beige/Beige GB				3-4	3-4	100	Cr	5	4-5	5	Ch	
								5	5	5	W	
								5	4-5	4-5	C	
TRUPOCOR Beige/Beige TM				3-4	2-3	100	Cr	5	4-5	3-4	Ch	
								5	3	4-5	W	
								4	4	4	C	
TRUPOCOR Beige/Beige LP				3-4	3	100	Cr	5	4-5	5	Ch	
								5	5	5	W	
								5	5	4-5	C	
TRUPOCOR Brown/Pardo THN				4-5	2	100	MF	4-5	4	4-5	Ch	
								5	4-5	5	W	
								5	4-5	5	C	
TRUPOCOR Brown/Pardo T5G-N				3-4	3	100	MF	5	4-5	3-4	Ch	
								5	3-4	5	W	
								3-4	3	3	C	
TRUPOXANE Brown/Pardo XF4				4	3-4	100	Cu	5	4	4	Ch	
								5	4-5	4-5	W	
								5	5	4-5	C	
TRUPOXANE Brown/Pardo GMG				3-4	3-4	100	Cr	4-5	4-5	5	Ch	
								5	4	4-5	W	
								4-5	3-4	3-4	C	
TRUPOXANE Brown/Pardo GMR				3-4	4	100	Cr	5	5	5	Ch	
								5	4-5	4-5	W	
								4-5	4	4-5	C	
TRUPOXANE Brown/Pardo 2MTE				3-4	3	100	Cr Cu	5	5	4-5	Ch	
								5	4-5	5	W	
								4-5	4-5	3	C	
TRUPOCOR Brown/Pardo THG				3	2-3	100	MF	4-5	4	5	Ch	
								5	5	4-5	W	
								3-4	4-5	4	C	

Dyestuff Colorante	Retained 0,5%	Retained 4,0%	Split	Penetration	Light	Solubility	Metal content	PVC	Perspiration	Washing	
								PUD			PUH
TRUPOCOR Brown/Pardo 5R				2-3	3	100	MF	4-5 4 2	4-5 3 3-4	3 4 C	Ch W C
TRUPOCOR Brown/Pardo TEN				4-5	2	100	MF	5 5 4-5	4 4 4-5	4-5 4-5 3-4	Ch W C
TRUPOCOR Brown/Pardo TS				5	2-3	100	MF	5 5 4-5	3-4 4-5 4	4-5 4-5 3	Ch W C
TRUPOCOR Dark Brown Pardo Oscuro FR-N				3-4	2-3	75	MF	5 5 3-4	5 4-5 3-4	4-5 5 3	Ch W C
TRUPOCOR Brown/Pardo GST-N				3-4	3-4	100	Cr	4-5 5 3	4-5 3 3	4-5 4-5 3	Ch W C
TRUPOXANE Brown/Pardo RTL				3-4	3	50	Cr Fe	3 5 3	4-5 4-5 4	4-5 4-5 3	Ch W C
TRUPOCOR Brown/Pardo TRB				4	3	50	MF	2 3-4 2	4 4 3-4	3-4 3-4 3	Ch W C
TRUPOCOR Brown/Pardo BBR				3-4	2-3	40	MF	4-5 5 2	5 4 3-4	4-5 4-5 3	Ch W C
TRUPOCOR Brown/Pardo B				2-3	3	75	MF	4-5 4-5 2	4 3 3	2 4 3-4	Ch W C

Dyestuff Colorante	Retained 0,5%	Retained 4,0%	Split	Penetration	Light	Solubility	Metal content	PVC	Perspiration		Washing	
								PUD	PUH			
TRUPOCOR Dark Brown Pardo Oscuro MX				2-3	2	75	MF	4-5 4 3	4 3-4 2-3	5 5 3-4	Ch W C	
TRUPOCOR Brown/Pardo HTB				3-4	2-3	50	Cr	5 5 4	5 3-4 3	3-4 5 3	Ch W C	
TRUPOXANE Brown/Pardo OBS				3-4	4	100	Cr	3 3-4 2	4-5 4-5 4	4 4-5 4	Ch W C	
TRUPOXANE Brown/Pardo OM				3-4	3-4	100	Cr	5 5 3	4 4 4	4-5 4-5 4-5	Ch W C	
TRUPOCOR Olive Brown Pardo Oliva GN				4	3-4	50	Fe	4-5 5 5	5 4-5 4	4 4 4	Ch W C	
TRUPOCOR Olive/Oliva 2G				3	3-4	75	Fe Cr	3-4 4-5 3-4	3-4 4 4-5	4 4-5 4-5	Ch W C	
TRUPOXANE Olive/Oliva RG				3	4	75	Cr	2-3 3-4 2	4 4 4	3 4-5 4-5	Ch W C	
TRUPOCOR Green/Verde NT				4	3	50	MF	5 5 4-5	5 3-4 3	4-5 4-5 3-4	Ch W C	
TRUPOCOR Green/Verde MN				4	3	100	Cu Cr	5 5 4	4-5 4 3-4	5 5 3-4	Ch W C	
TRUPOCOR Green/Verde BBO				3-4	4	100	Cu	4-5 5 4-5	5 4-5 4	5 5 4-5	Ch W C	

Dyestuff Colorante	Retained 0,5%	Retained 4,0%	Split	Penetration	Light	Solubility	Metal content	PVC	Perspiration		Washing	
								PUD	PUH			
TRUPOCOR Turquoise Azul Turquesa FBP				4	4	75	Cu	5	4-5	4-5	Ch	
								5	3-4	5	W	
								5	3	3-4	C	
TRUPOCOR Blue/Azul FNL				2-3	2	100	MF	4	4	3	Ch	
								5	4	4	W	
								2	4	3	C	
TRUPOCOR Violet/Violeta 4BR				4	1	50	Cu	2-3	4	1-2	Ch	
								3-4	3	5	W	
								1	3	4-5	C	
TRUPOCOR Violet/Violeta R-1192				3-4	1-2	100	MF	4	5	2	Ch	
								4-5	4	4-5	W	
								2-3	3-4	4	C	
TRUPOCOR Blue/Azul GR				3	2-3	100	MF	4	4-5	2-3	Ch	
								4-5	3	3	W	
								2	3	3	C	
TRUPOCOR Navy blue Azul Marino N2B				3-4	2-3	100	MF	4-5	4-5	2	Ch	
								4	4-5	4-5	W	
								2	4-5	4	C	
TRUPOCOR Navy blue Azul Marino B				4	2-3	50	MF	4-5	4-5	3-4	Ch	
								4-5	3	3	W	
								2	3	3	C	
TRUPOCOR Blue/Azul N2C				3-4	4	100	Cr	3-4	4	3-4	Ch	
								5	3	4-5	W	
								2	2-3	3	C	

Dyestuff Colorante	Retanned 0,5%	Retanned 4,0%	Split	Penetration	Light	Solubility	Metal content	PVC	Perspiration		Washing	
								PUD				
TRUPOCOR Grey/Gris STL				4	3	100	Cr	5	4-5	4-5	Ch	
								5	5	5	W	
								5	5	4-5	C	
TRUPOCOR Grey/Gris PRL				4	3-4	100	Cr	5	5	4-5	Ch	
								5	5	5	W	
								4-5	4-5	4-5	C	
TRUPOXANE Grey/Gris TL				2-3	3	100	Cr	5	4-5	3-4	Ch	
								5	4-5	5	W	
								4-5	4-5	5	C	
TRUPOXANE Grey/Gris TD				2-3	3	100	Cr	4-5	4	4	Ch	
								5	5	5	W	
								4	4-5	5	C	
TRUPOCOR Grey/Gris TG				3-4	3	100	Cr	4-5	4	3-4	Ch	
								5	4-5	5	W	
								4	4-5	5	C	
TRUPOCOR Grey/Gris T-99				4	3	50	Cr	4	4-5	4-5	Ch	
								5	4-5	4-5	W	
								3	4-5	4	C	

Dyestuff Colorante	Retanned 0,5%	Retanned 4,0%	Split	Penetration	Light	Solubility	Metal content	Perspiration			Washing
								PVC	PUD	PUH	
TRUOCOR Black/Negro P-SG				5	5	100	MF	5	5	4	Ch
								5	5	5	W
								5	5	5	C
TRUOCOR Black/Negro MJ				5	3-4	75	MF	5	4-5	4	Ch
								4-5	5	5	W
								4	5	4-5	C
TRUOCOR Black/Negro HFT				4	4	100	Cr	5	4-5	4-5	Ch
								5	3-4	4-5	W
								4	3-4	3	C
TRUOCOR Black/Negro BDB				3-4	2-3	75	MF	5	4-5	4-5	Ch
								5	3-4	3-4	W
								4	2-3	2-3	C
TRUOCOR Black/Negro RT				3	2	100	MF	5	4	4	Ch
								5	3-4	5	W
								3-4	3-4	2-3	C
TRUOCOR Black/Negro T				2-3	3	100	MF	4-5	4-5	4-5	Ch
								4-5	4-5	4	W
								3	3-4	3	C
TRUOCOR Black/Negro T-extra				2-3	3	100	MF	4-5	5	4	Ch
								4-5	4-5	4	W
								3	4	3	C
TRUOCOR Black/Negro MC extra				4	4	75	Cr	3-4	4-5	4-5	Ch
								3	3	4	W
								2	2-3	3-4	C
TRUOCOR Black/Negro TZ				3-4	3	100	MF	5	5	5	Ch
								5	4	5	W
								3	3	3-4	C